



# PLUS

## Floor Finish & Cleaner/Maintainer

### INSTRUCTIONS FOR RESTORATION

When your floor has been subjected to heavy use or chemicals that mark or damage the Hilway Direct Plus Floor Finish. The following instructions will help you repair those areas and bring the floor back to its original sheen.

#### Repairing scuffs and wear in the finish

1. Dry sweep then damp mop the floor to remove loose dirt and soil from the floor. Thoroughly clean floor with Hilway Direct Neutral Cleaner mixed 1:10 (1 part cleaner to 10 parts water) and a 3M 5100 red pad or equivalent then rinse the floor with clean water. Let the floor dry.
2. Mix **Hilway Direct Plus** in a spray bottle 1:5. (1 part **Hilway Direct Plus** with 5 parts water)
3. Spray a heavy amount of the solution on the floor, working in 4'x4' areas. Wipe on the solution with a clean microfiber mop. Repeat this process 2-3 times. Allow to dry completely between each application (approx 30min to an hour depending on temperature and humidity)

#### Repairing a damaged area due to excessive wear or chemical spills

1. Clean the area immediately with clean water and a clean sponge or cloth.
2. Thoroughly clean the area with Hilway Direct Neutral Cleaner mixed 1:10 and a 3M 5100 red pad or equivalent, then rinse the floor with clean water. Let the floor dry.
3. Pour on to the damaged area the Hilway Direct Plus full strength. Use a microfiber cloth to uniformly spread the finish in the damaged area.
4. Allow the **Hilway Direct Plus** to dwell for 1 minute.
5. After 1 minute of dwell time rub the finish using sponge or microfiber cloth in a circular motion and pressing down firmly to feather the finish around the edge of the damaged area.
6. Then smooth it out evenly.
7. Repeat this 2 -3 times in the damaged area allowing the area to dry completely between applications (approx 1-2 hrs depending on temperature and humidity).
8. Mix **Hilway Direct Plus** in a spray bottle 1:5. (1 part **Hilway Direct Plus** with 5 parts water)
9. Spray the mixed solution in damaged area and wipe with a clean microfiber mop. Repeat this process 2-3 times to achieve the desired look.

**Note: You will notice marked improvement in the area. However, extreme distortion may require complete removal using Hilway Direct AllSafe Stripper and reapplying 2-3 coats of Hilway Direct Plus.**